



Excellent System A/S  
Attn.: Ole Frederiksen  
Postboks 32  
DK-8444 Mørke

Teknologiparken  
Kongsvang Allé 29  
DK-8000 Århus C  
Telefon 72 20 10 00  
Telefax 72 20 10 19

info@teknologisk.dk  
www.teknologisk.dk

Aarhus 21<sup>st</sup> September 2000  
jda/rna

### **Test of Excellent comfort standard tile, measures: 250x250x18 mm**

We hereby certify that above mentioned product has been tested 4<sup>th</sup> October 1992 according to below method.

**Test method:**

Measuring of flashover voltage with a Holliday Detector.

The flag element is in a dry room on a dry metal sheet. The flashover voltage is measured between a brush-shaped electrode placed at the middle of the tile and the metal sheet. The voltage can be adjusted in steps of 1.000 V.

**Test result:**

There was no flashover at 13.000 V.

When building a floor with several layers, the flashover voltage on new-laid tiles per layer will amount to a minimum of 13.000 V.

	Flashover voltage
1 layer of Excellent comfort standard tile	13.000 V
2 layers of Excellent comfort standard tile	26.000 V
3 layers of Excellent comfort standard tile	39.000 V

Yours sincerely  
Product Development

Jørgen Daugaard  
Engineer

**Teknologisk Institut**  
Teknologiparken  
Kongsvang allé 29  
DK-8000 Århus C

Telephone: +45 7220 1680 (direct number)  
Telefax: +45 7220 1717  
E\_mail: jorgen.daugaard@teknologisk.dk